

Compound Data

Compound	Indicitive Temp Range	Shore Hardness
Nitrile 70	-30°C to +120°C	70
	(peak +140°C)	
FPM75	-10°C to +200°C	75
	(peak +250°C)	
Nitrile 90	-20°C to +120°C	90
	(peak +140°C)	
Nitrile 60	-30°C to +120°C	60
	(peak +140°C)	
Nitrile 80	-20°C to +120°C	80
	(peak +140°C)	
FPM75 Brown	-10°C to +200°C	75
	(peak +250°C)	
FPM75 Green	-10°C to +200°C	75
	(peak +250°C)	
FPM90	-10°C to +200°C	90
	(peak +250°C)	
Silicone 70	-60°C to +200°C	70
EPDM FDA Peroxide Cured Grey	-55°C to +150°C	70
	(peak +170°C)	
EPDM WRAS Approved	-50°C to +120°C	70
EPDM Peroxide Cured Black	-60°C to +150°C	70
	(peak +170°C)	
EPDM Sulphur Cured Black	-50°C to +110°C	70
	(peak +130°C)	
FEP + FPM	+204°C to -60°C	75
FEP + SIL	+220°C to -60°C	70
PTFE O Rings	-50°C to +260°C	
Lip Seal NBR75	+120°C to -20°C	75
	(peak +140°C)	
Lip Seals NBR90	+120°C to -15°C	90
	(peak +140°C)	
Lip Seals NBR85	+120°C to -15°C	85
	(peak +140°C)	
Oil Seals NBR75	+120°C to -25°C	75
	(peak +140°C)	
Oil Seals FPM75	+200°C to -10°C	75
	(peak +250°C)	

